International Journal of Zoology and Applied Biosciences Volume 10, Issue 3, pp: 68-73, 2025 https://doi.org/10.55126/ijzab.2025.v10.i03.008



http://www.ijzab.com

ISSN: 2455-9571

Rishan

GREEN SYNTHESIS OF SILVER NANOPARTICLES USING SOME MEDICINAL PLANT LEAVES EXTRACT AND STUDY OF ITS ANTIBACTERIAL ACTIVITY

*Nisha Singh and Shivani Tiwari

Department of Chemistry, Govt. M. H. College of Home Science and Science for Women, (Autonomous) Jabalpur M.P., Jabalpur-482001, India.

Article History: Received 28th March 2025; Accepted 31st April 2025; Published 31st May 2025

ABSTRACT

The synthesis of silver nanoparticles (AgNPs) using plant extracts has gained attention due to its eco-friendly approach and antimicrobial properties. In this study, AgNPs were synthesized using leaf extracts of *Ficus religiosa* (Peepal) and evaluated for antibacterial activity against *Escherichia coli* using the well diffusion method. The antibacterial activity varied across different concentrations. The formation of AgNPs was confirmed using UV-Vie ab orption spectroscopy (200-600 µm), and their particle size was determined using a particle size analyzer. The results indicite that *Ficu religiosa* is an effective source for AgNPs biosynthesis, with potential applications in various scientific and industrial fields, this protocol as simple, rapid, one step, eco-friendly, nontoxic and an alternative conventional physical/chemical method. Only 24hrs. Were required for the conversion of silver ions into silver nanoparticles at room temperature, without the involvement of any hazardous chemical.

Keywords: Silver nanoparticles, Well diffusion assay, Medicinal plants, Antibacterial activity, Green synthesis.

INTRODUCTION

The 'green' environment friendly processes in chemistry and chemical technologies are becoming increasingly popular and are much needed as a result of worldwide problems associated with environmental concerns (Thuesombat et al., 2014). Silver is the one of the most commercialised nano-material with five hundred tons of silver nanoparticles production per year (Larue et al., 2014) and is estimated to increase in next few years. Including its profound role in field of high sensitivity biomolecular detection, catalysis, biosensors and medicine; it is been acknowledged to have strong inhibitory and bactericidal along with the anti-fungal, anti-inflammatory and antiangiogenesis activities (El-Chaghaby & Ahmad, 2011; Veerasamy et al., 2011). Conventional chemical methods for AgNP synthesis often involve hazardous chemicals, high energy consumption, and the generation of toxic byproducts, raising environmental concerns. In contrast, biological or "green" synthesis, utilizing natural resources such as microorganisms, enzymes, and plant extracts, offers a sustainable, cost-effective, and eco-friendly alternative (Iravani *et al.*, 2014). Plant extracts, rich in various bioactive compounds like polyphenols, flavonoids, terpenoids, and alkaloids, act as both reducing and stabilizing agents in the synthesis of AgNPs, eliminating the need for external toxic chemicals.

Nanoparticles represent completely new and improved properties based on specific characteristics such as size distribution andmorphology (Logeswari and Abraham, 2015). Nanoparticles are synthesized by two different ways: Chemical and Biological. Chemical synthesis of nanoparticles leads to synthesis of environmentally toxic byproducts but production of silver nanoparticles from green extracts including bark, leaf, root etc is nontoxic and has effective stability (Prasad et al., 2012). Thus, the best and the most ecofriendly way tosynthesized nanoparticles is a biological method. Biological way is simple, fast and economical. Moreover, this green technology does not involve any toxic chemicals (Zhang et al., 2016). The nanoparticles are characterized by using UV-Vis

*Corresponding Author: Nisha Singh, Department of Chemistry, Govt. M. H. College of Home Science and Science for Women, (Autonomous) Jabalpur M.P., Jabalpur- 482001, India Email: nishasingh07061989@gmail.com

spectroscopy. Medicinal plants have been traditionally used for centuries to treat various ailments, including infections, due to their inherent antimicrobial properties. Integrating the antimicrobial potential of medicinal plant extracts with the enhanced antibacterial activity of AgNPs through biosynthesis presents a synergistic approach to develop novel and effective antibacterial agents. This research focuses on the biosynthesis of AgNPs using extracts from selected medicinal plants known for their traditional use in treating infections. The study aims to screen the antibacterial potential of these biosynthesized AgNPs against clinically relevant bacterial pathogens and compare their efficacy with that of the crude plant extracts. In this present study, silver nanoparticles were synthesized using the leaf extract of Ficus Religiosa, which is a traditional medicinal tropical plant. Ficus Religiosa commonly referred to as Peepal tree, sacred tree or Bodhi tree an evergreen tree belonging to family of Moraceae family (fig or mulberry family). Silver nanoparticles can be inhibitory to various microorganisms.

MATERIALS AND METHOD

Survey and collection of plant leaves

In the present research work, the plant sample was collected from the various regions of the Jabalpur regions such as Govt. M.H. College of Home Science campus of Jabalpur region. The collected leaves were used in the preparation of extracts for the green synthesis of AgNPs, and the evaluation of their biological activities.

Table 1. Select Indian medicinal plant used to treat various kinds of human.

| S. No. | Common name | Medicinal plant | Part of | |
|--------|-------------|------------------|------------|--|
| | | (Botanical name) | plant used | Ayurvedic or Traditional Uses |
| 1 | Peepal Tree | Ficus Religiosa | Leaves | Leaves of plant are used to treat Stomach pain, Asthma, Skin diseases, Eczema itching, Blood purification, Liver and spline disease, Swelling in Spline and Hiccups |

Phytochemistry



protein, lipid, calcium, sodium, potassium, and phosphorus. (Ruby *et al.*, 2008) The aqueous extract of dried bark of *F*. *religiosa* has been reported to contain phytosterols flavonoids, tagnins, furanocounarin rerivitives tameb bergapten and begaptol.

Preparation of plant metabolite

Fresh leaves of medicinal plant Peepal (*Ficus Religiosa*) were collected from Govt. M.H. College of Home Science campus of Jabalpur region. The leaves were rinsed with sterilized distilled water & ethanol and air dried under shade for 10 days. Then the plant leaves were grind into fine powder. Then take 5gm of the leaf powder was mixed with 100ml distilled water then boil for 10 min., after boiling, the mixture was cooled and filtered with Whatman filter paper number 1 used for synthesis of silver nanoparticles.



Bio-Synthesis of silver nanoparticles

In the present study, 1mM aqueous solution of silver nitrate (AgNO₃) was prepared and used for the synthesis of silver nanoparticles. For synthesis of silver nanoparticles 50 ml filtrate distilled water & ethanol of leaf extract of *Ficus Religiosa* was added for bio-reduction process at room temperature in dark condition for 24 hours. After the proper incubation period the change of color was observed visually (green & dark brown colour).

Agar well diffusion method

The antibacterial bioassay was performed by Agar well diffusion method given by Egrov, (1995) against pathogenic bacteria Escherichia coli. The nutrient agars plates were prepared and well of 8mm were made in the plates with the help of a cork borer. Nutrient agar plates were seeded with two sets 20µl (DW) & 40µl (Ethanol) of standardized broth culture of the test bacteria. Each plate was spread evenly on the plate bacterial solution and after 20 min of spreading; the wells were loaded with 100 µl plant metabolites. The Petri plates were then placed in an incubator at 37°C, and the antibacterial activity of AgNPs was evaluated by measuring the diameter of the zone of inhibition (in cm) surrounding and the wells measured with the help of Hi-media antibiotic zone scale, at Mata Gujri Mahila Mahavidyalaya (Autonomous) Jabalpur., indicating of the other nanoparticles. the antipriorobial effectivenes

RESULT AND DISCUSSION

In the present study, potential of Ficus Religiosa leaves extract was used to synthesize AgNPs. The synthesized AgNPs were characterized using UV-visible spectroscopy and the antibacterial activities of these AgNPs were evaluated. Antibacterial activity of the plant metabolites extract was determined by agar well diffusion method against the test Escherichia coli (MTCC1679) bacterial strain. The Ficus Religiosa plant metabolite was showed the maximum zone of inhibition against Escherichia coli (MTCC1679) 24mm in 20µl (DW), 40mm in 40µl (DW), 11mm in 20µl (Ethanol) and 11mm in 40µl (Ethanol) as shown in table. 4.2, graph 4.1 and plate 4.3. Similarly, leaf extracts of A. officinalis were examined for its antibacterial potential using five different solvents against some reference strains of human pathogenic bacteria for the crude extract and showed remarkable antibacterial activity with zones of inhibition of 13mm against Eschericia coli and 11mm against Staphylococcus aureus. Fraction 13(ethyl acetate: methanol 8:2) as the most potent one against with the minimal inhibitory concentration of 30 mm against E. coli and 25 mm against S. aureux (Bhimba et al., 2010).

The *Ficus Religiosa* plant metabolite mixed with in the aqueous solution ion complex, color change from light green to dark brown was observed due to the reduction of silver ions as in Figure 2. The color change is reportedly confirmation of formation of nano-particles. The change of color of silver nanoparticles was observed after the 24 hrs of dark metabal or of the sample on the rotaty strates



Figure 2. Biosynthesis of silver nanoparticles from plant leaf extract.

Table 2. Characterization of bio synthesized silver nanoparticles on the basis of colour change.

| Name of Bacterial strain isolates | Name of Host plant | Colour change |
|-----------------------------------|--------------------|---------------|
| Escherichia coli (MTCC1679) | Ficus religiosa | Brown colour |

Table 3. Spectrophotometric analysis of biosynthesized silver nanoparticles on the basis of absorbance (200nm-600nm).

| Molar solution of AgNO ₃ for different | Range of wavelength | Absorbance (in nm) | |
|---|---------------------|--------------------|--|
| plant leaves extract | (200-600) | | |
| 1mM AgNO ₃ | 422 | 3.116(ethanol) | |
| (Ficus Religiosa) | 400 | 3.731(DW) | |



Graph 1. UV- Spectroscopy of 1mM AgNO3Ficus Religiosa Biosynthesized silver nanoparticles.

After the biosynthesis of silver nanoparticles by using leaf extract were further characterized by using various approaches such as UV-Visible spectrophotometer to detect me absorbance on the nanoparticles. The findings from the Vi absorption spectrum were considered as rouge UVennique widely used for structural characterization of nanoparticles. In case reduction of silver nanoparticles during exposure to fungal metabolite was observed as a result of the color change. The color change is due to the SPR phenomenon. The SPR pattern is dependent on the characteristics of the individual metal particles, such as size and shape, as well as the dielectric properties of the medium used for synthesis and the inter-nanoparticle coupling interactions. The intensity of the SPR band increased with reaction time, indicating the synthesis of the AgNPs.

Similarly, the formation of silver nanoparticles synthesized from Ocimum tenuiflorum, Solanum tricobatum, Syzygium cumini, Centella asiatica and Citrus sinensis were monitored by UV-vis spectrophotometer analysis. The UV-vis spectra showed maximum absorbance at 420 nm, which increased with time of incubation of silver nitrate with the plants extract. The curve shows increased absorbance in various time intervals (1 h, 24 h and 48 h) and the peaks were noticed at 420 nm corresponding to the surface plasmon resonance of silver nanoparticles. The observation indicated that the reduction of the Ag+ ions tock place extraconum rly (Logeswari *et al.*, 2011).

The antibacterial efficacy of the silver nanoperticles /คร confirmed by the formation of a zone of inhibition around the well (Figure 5). The antibacterial activity of biosynthesized silver nanoparticles from the plant leaves extract of Ficus Religiosawas studied against bacterial Escherichia coli (MTCC1679). The strain silver nanoparticles of Ficus Religiosawas showed the maximum zone of inhibition against Escherichia coli (MTCC1679) as shown in figure 3, table 4, graph 2. Similarly (Pranab et al., 2024) studied the La₂O₃ and CeO₂ nanoparticles were successfully synthesized using an aqueous extract of Ficus religiosa leaves. UV-Visible, FTIR, and PXRD analysis confirmed the optical behaviour, vibrational modes, and size of synthesized La₂O₃ and CeO₂ NPs. The antibacterial activity of synthesized nanoparticles was performed against overnight grown bacteria to view its inhibited growth zone. The antioxidant activity of synthesized NPs exhibits good results and may have potential applications in the field of biomedicine and material science.

Table 4. Zone of inhibition in mm against Escherichia coli (MTCC1679).

| | Zone of inhibition Escherichia coli (MTCC1679) | | | | | | | |
|-----------------|--|---------------------------------|-----------|-----------|--|--|--|--|
| Plant sample | 20µl | 40µl (Distilled Water) | 20µl | 40µl | | | | |
| - | (Distilled Water) | | (Ethanol) | (Ethanol) | | | | |
| Ficus Religiosa | 24mm | 40mm (Bacterial growth inhibit) | 11mm | 11mm | | | | |



Figure 3. Screening of Silver Nanoparticles for Antibacterial Activity.



Graph 2. Antibacterial activity of biosynthesized silver nanoparticles.

Dr.

green synthesis of s lver nanoparticles offers potentially, ecofriendly, non-toxic, and cost-effective approach for the synthesis of nanoparticles. Different plant extracts can be used for the synthesis of silver nanoparticles. In the present research work the plant extract of Ficus Religiosa was used for the synthesis of silver nanoparticles. The antibacterial activity was examined against the test bacterial strain Escherichia coli (MTCC 1679). It is understood that different types of natural compounds present in plant extracts can act as reducing and stabilizing agents in the synthesis of silver nanoparticles. Furthermore, silver nanoparticles generated by green synthesis have potential applications, especially as antibacterial agents of certain microorganisms for which their efficiency has been scientifically proven, in biomedicine as therapeutic agents and wastewater treatment, in agriculture, in food safety and in food packaging. Therefore, the green synthesis of silver nanoparticles from Ficus Religiosa leaves extracts has several advantages such as eco-friendly, biocompatibility and cost-effectiveness. It is concluded that due to these unique properties, silver nanoparticles will have a key role in many of the nanotechnology-based processes.

ACKNOWLEGMENT

CONCLUSION

I sincerely express my gratitude to Dr. Sameer Shukla (Principal) Govt. M. H. College of Home science and science for women Autonomous Jabalpur (M.P.), Dr. Kiran Singh (HOD Department of Chemistry), and my supervisor

encoaragement and constant support throughout reh work. Their insights and expertise have been instrumental in shaping this work. I am especially grateful Shyam Shukla (Coordinator, Dept. to Dr. of Biotechnology) Mata Gujri Mahila Mahavidyalaya (Autonomous) College, Jabalpur, for providing laboratory facilities and valuable direction, which greatly contributed to the successful completion of my work. Above all, I express my profound gratitude to my family for their unwavering support, motivation, and belief in me, which has been a driving force in completing this study.

Nvaluable guidance.

CONFLICT OF INTERESTS

The authors declare no conflict of interest

Nisha Singh for their

ETHICS APPROVAL

Not applicable

AI TOOL DECLARATION

The authors declares that no AI and related tools are used to write the scientific content of this manuscript.

DATA AVAILABILITY

Data will be available on request

REFERENCES

- AI Egorov (1995). The scientific heritage of I. P. Egorov. July 25. Volume 74, pages 977-996.
- Bhimba, B. V., Meenupriya, J., Joel, E. L., Naveena, D. E., Kumar, S., & Thangaraj, M. (2010). Antibacterial activity and characterization of secondary metabolites isolated from mangrove plant Avicennia officinalis, *Asian Pacific Journal of Tropical Medicine*, 3(7), 544-546.
- Bushra S, Farooq A. Flavonols (kaempeferol, quercetin, myricetin) 2008. Contents of selected fruits, vegetables and medicinal plants. *Food Chemidtry*, 108, 879-84.
- El-Chaghaby, G. A., & Ahmad, A. F. (2011). Biosynthesis of silver nanoparticles using pistacia lentiscus leaves extract and investigation of their antimicrobial effect. *Oriental Journal of Chemistry*, 27, 929e936.
- Khare C. P. (2004). Encyclopedia of Indian medicinal plants. Berlin Heidelberg, New York: Springer Verlag;. pp.50-8.
- Larue, C., Castillo-Michel, H., Sobanska, S., Cecillon, L., Bureau, S., Barth_es, V., et al. (2014). Foliar exposure of the crop Lactuca sativa to silver nanoparticles: evidence for internalization and changes in Ag speciation. *Journal of Hazardous Materials*, 264, 98e106.
- Logeswari, P. and Abraham, J. (2015). Synthesis of silver nanoparticles using plants extract and analysis of their antimicrobial property. *Journal of Saudi Chemical Society*. 19(3), 311-317.
- Oliver bever B. (1977). Oral hypoglycaemic plants in West Africa. *Journal of Ethpopharmacology*, 2,119-27.

- Pranali Parab, Aniket Pawanoji & Amol PawarPranali Parab, Aniket Pawanoji & Amol Pawar (2024). Peepal (Ficus religiosa) leaf extract mediated green synthesis of lanthanum and cerium oxide nanoparticles: Characterization and potential biological applications. *Indian Journal of Chemistry*, 63, pp. 15-20.
- Ruby J., Nathan P.T., Balasingh J., Kunz T. H. (2000) Chemical composition of fruits and leaves eaten by shortnosed fruit bat, *Cynopterus sphinx*. *Journal of Chemical Ecology*, 26,2825-41.
- S. Iravani, H. Korbekandi, S. V. Mirmohammadi, B. Zolfaghari (2014). Synthesis of silver nanoparticles: chemical, physical and biological methods, *Research in Pharmaceutical Sciences*, 9(6),385-406.
- Sheetal A, Bagul MS, Prabia M, Rajani M.(2008). Evaluation of free radicals scavenging activity of an Ayurvedic formulation, panchvankala. *Indian Journal of Pharmactical Science*, 70,31-8.
- Thuesombat, P., Hannongbua, S., Akasit, S., & Chadchawan, S. (2014). Ecotoxicology and environmental safety effect of silver nanoparticles on rice (Oryza sativa L. cv. KDML 105) seed germination and seedling growth. *Ecotoxicology and Environmental Safety*, 104, 302e309.
- Zhang, X.F., Liu, Z.G., Shen, W., and Gurunathan, S. (2016). Silver Nanoparticles: Synthesis, characterization, properties, applications and therapeutic approaches. *International Journal of Molecular Sciences*, 17 (9), 1534.
- Online First Copy